



PC1/GB 2003 / 0 0 0 8 3 2



INVESTOR IN PEOPLE

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

#2

PRIORITY DOCUMENT
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH
RULE 17.1(a) OR (b)

REC'D 08 MAY 2003

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) Part (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

Signed

Dated 10 April 2003


The
**Patent
Office**

06MAR02 E700990-1 000032
P01/7700 0.00-0205151.4

Patents Act 1977
(Rule 16)

Request for grant of a patent

(See the notes on the back of this form. You can also get
an explanatory leaflet from the Patent Office to help
you fill in this form)



5 MAR 2002

The Patent Office

Cardiff Road
Newport
Gwent NP9 1RH

1. Your reference **REG/P17342GB**

2. Patent application number **0205151.4**
(The Patent Office will fill in this part)

3. Full name, address and postcode of the or of each applicant (underline all surnames)

(1) Sericol Limited **7340730001**
Patricia Way
Pysons Road Industrial Estate
Broadstairs
Kent, CT10 2LE

(2) Dotrix nv **8337818001**
Tramstraat 69
B-9052 Gent
Belgium

Patents ADP number (if you know it)

If the applicant is a corporate body, give the
country/state of its incorporation

(1) United Kingdom (2) Belgium

4. Title of the invention **An ink-jet ink printing process and ink-jet inks used therein**

5. Name of your agent (if you have one) **ELKINGTON AND FIFE**

"Address for service" in the United Kingdom
to which all correspondence should be sent
(including the postcode)

**ELKINGTON AND FIFE
PROSPECT HOUSE
8 PEMBROKE ROAD
SEVENOAKS
KENT
TN13 1XR**

Patents ADP number (if you know it)

67004

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or each of these earlier applications and (if you know it) the or each application number	Country	Priority application number (if you know it)	Date of Filing (day/month/year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application	Number of earlier application	Date of Filing (day/month/year)

Patents Form 1/77

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer "Yes" if:

Yes

- a) any applicant named in part 3 is not an inventor, or
- b) there is an inventor who is not named as an applicant, or
- c) any named applicant is a corporate body.

See note (d))

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

-

Description

11

Claim(s)

2

Abstract

-

Drawing(s)

-

10. If you are also filing any of the following, state how many against each item.

Priority documents

-

Translations of priority documents

-

Statement of inventorship and right to grant of a patent (Patents Form 7/77)

-

Request for preliminary examination and search (Patents Form 9/77)

-

Request for substantive examination (Patents Form 10/77)

-

Any other documents (please specify)

-

11.

I/We request the grant of a patent on the basis of this application.

Richard Gillard

Signature
Richard Gillard

Date
05 March 2002

12. Name and daytime telephone number of person to contact in the United Kingdom

Richard Gillard
020 7405 3505

An ink-jet ink printing process and ink-jet inks used therein

The present invention relates to an ink-jet ink printing process and in particular to the provision of an improved process for wet-on-wet ink-jet printing.

5

In ink-jet printing, minute droplets of ink are ejected in a controlled manner from one or more reservoirs or printing heads through nozzles onto a substrate, which is moving relative to the reservoirs. The ejected ink forms an image on the substrate. For high-speed printing, the inks must flow rapidly from the printing heads and this puts a number of constraints on the physical properties of the ink. These constraints include a low viscosity which for piezoelectric Drop-on-Demand (DOD) ink-jet printing is usually 1-50 mPas, preferably 6-30 mPas, particularly preferably 8-15 mPas (at the jetting temperature which may be from 25 to 110°C.), and a surface tension such that the jet can form the necessary small droplets (10-50 dyne/cm, preferably 25-35 dyne/cm). The ink must also be a homogenous liquid capable of rapid conversion to a dry printed area. The particles of pigment dispersed therein should have a particle size of less than 8 μm , preferably less than 3 μm and particularly preferably less than 1 μm .

The concept of piezoelectric ink-jet printing is based on the movement of a piezoelectric ceramic transducer when a voltage is applied thereto. When the voltage is applied, the shape of the ceramic changes, creating a void, which is filled with ink. When the voltage is then removed, the ceramic expands to its original shape, ejecting a drop of ink from the print head.

The printing system generally used is a flexible single pass unit with piezoelectric heads. One ink drop can therefore be printed onto another without intermediate solidification of the first ink drop. This is known as wet-on-wet printing. The phrase "without intermediate solidification" is understood in the art to mean that the first or subsequent ink drop is still liquid when the next ink drop is applied. In order to avoid curing the first or subsequent ink drops before the next ink drop is applied, the first or subsequent ink drops are not cured, i.e. they are not irradiated prior to application of the next ink drop.

Wet-on-wet printing is primarily used in colour printing to apply ink drops of differing colours sequentially to the same area of the substrate which then combine to produce the desired colour. The typical four-colour set is Cyan, Magenta, Yellow, and Black known as C-M-Y-K but the technique is extendable to six-colour hexachrome or any progressive dot printing ink-jet process. The inks used are known 100% solids UV pigmented inks.

Good print definition quality requires the following: a rapid formation of a solid coloured dot from the ink composition; concentration of the ink colourants on the surface of the substrate without being absorbed into the substrate surface; control of the spread of the dot of colour formed on the surface of the substrate; limited merging or bleed of the ink of one colour from a dot to a neighbouring dot of a different colour; and uniformity of colour and colour density over the solid area of print formed from the droplets.

The most common problems associated with wet-on-wet printing are mottling, puddling and the lack of sharp lines. Mottling and puddling are related to the printing of solid areas when the colour density varies across the area of print. The sharpness of line edges is important in achieving clear images in, for example, text.

Accordingly, the present invention provides a progressive dot printing ink-jet process comprising the steps of applying a first ink drop to a substrate and subsequently applying a second ink drop on to the first ink drop without intermediate solidification of the first ink drop, wherein the first and second ink drops have a different viscosity, surface tension or curing speed.

Preferably, further ink drops are applied sequentially to the first and second ink drops without intermediate solidification of the combined first and subsequent ink drops.

Preferably, at least four ink drops are applied sequentially.

Preferably, the first and subsequent ink drops are different colours.

Preferably, the ink drops are cyan, magenta, yellow and black.

Preferably, the viscosity of the first and last ink drops applied varies in a graduated
5 manner within a range of from 10 up to 30 mPas or 30 down to 10 mPas.

Preferably, the surface tension of the first and last ink drops applied varies in a graduated
manner within a range of from 20 up to 40 dynes/cm or 40 down to 20 dynes/cm.

10 Preferably, the cure speed of the first and last ink drops applied varies in a graduated
manner within a range of from 20 up to 70 m/min or 70 down to 20 m/min.

In another embodiment, the present invention also provides a set of ink-jet inks suitable
for use in a progressive dot printing ink-jet process comprising at least two inks having a
15 different viscosity, surface tension or curing speed.

In a further embodiment, the present invention also provides an ink dispenser holding a
set of ink-jet inks.

20 The ink compositions of the present invention include at least three main components.
These are (i) monomers and/or oligomers, (ii) photoinitiators, and (iii) colourant(s),
preferably a pigment. In addition, the inks may, optionally, contain surfactant and
synergist additives.

25 Monomers, oligomers or prepolymers may possess different degrees of functionality, and
a mixture including combinations of mono-, di-, tri- and higher functionality monomers,
oligomers or prepolymers may be used. These components are curable, typically
photocurable, e.g. UV curable, and should adhere to the substrate surface after printing
and serve to bind the pigment. Also adjusting the ratio of the monomers or oligomers is a
30 method of adjusting the viscosity of the ink. To obtain a gradient of viscosity the ratio
between monomers and oligomers is modified. A higher functionality results in a higher

viscosity. The viscosity varies in graduations from the most viscous ink to the least viscous ink or vice versa. Preferably, the viscosity varies from 10 up to 30 mPas or 30 down to 10 mPas, particularly preferably from 12 up to 22 mPas or 22 down to 12 mPas. The viscosity is measured using standard techniques known in the art.

5

Additionally, improvements in print quality may be achieved using a gradient of surface tension across the progressive colours (e.g. C-M-Y-K). To obtain a gradient of surface tension the ratio of monomers, oligomers or prepolymers is modified and also surfactant additives are used to lower the surface tension. Preferably, the surface tension varies
10 from 20 up to 40 dynes/cm or 40 down to 20 dynes/cm. Particularly preferably from 22 up to 31 dynes/cm or 31 down to 22 dynes/cm. The surface tension is measured using standard techniques known in the art.

Furthermore, improvements in print quality are achieved using a gradient of cure speeds
15 across the progressive colours (e.g. C-M-Y-K). To obtain a gradient in cure speeds the initiators and synergist additives are modified. Preferably, the cure speed varies from 20 up to 70 meters (m)/min or 70 down to 20 m/min. Particularly preferably from 30 up to 50 m/min or 50 down to 30 m/min. Measurements are made on a 12 μ m film of ink coated onto rigid PVC and passed under a 120 W/cm medium pressure mercury lamp.

20

Although the viscosity, surface tension or cure speed of the first and subsequent drops may vary in graduations from low to high or high to low, it is preferred that the first and subsequent drops increase in viscosity, i.e. that the first and subsequent drops vary in graduations from least viscous to most viscous, and that the surface tension of the drops
25 and the cure speed decreases from the first to the last ink printed, i.e. from highest surface tension to lowest surface tension and from highest cure speed to lowest cure speed.

The monomers, oligomers or prepolymers (i) are typically monofunctional and/or polyfunctional acrylate monomers, oligomers or prepolymers, such as an ester of acrylic
30 or methacrylic acid, such as octyl acrylate, decyl acrylate, hydroxyethyl methacrylate lauryl acrylate, phenoxyethyl acrylate, hexanediol diacrylate, polyethylene glycol

diacrylate, tri(propylene glycol) triacrylate, trimethylolpropane triacrylate, bis(pentaerythritol) hexa-acrylate; or an N-vinylamide such as, N-vinylcaprolactam or N-vinylformamide; or acrylamide or a substituted acrylamide, such as acryloylmorpholine. Preferred monomers, oligomers or prepolymers are the acrylate esters of the ethoxylated or propoxylated derivatives of di-, tri- or tetrahydric aliphatic alcohols, and the acrylate or methacrylate esters of epoxy, urethane, melamine or polyester resins or their ethoxylated or propoxylated derivatives.

These components may be sold under the names: Ebecryl 40, Ebecryl 1039, DPGDA, TPGDA, ODA-n, TTEGDA, Ebecryl 160, OTA 480, IRR 289, TMPTA, IRR 184, Ebecryl 111, Ebecryl 110, IBOA, HDDA, Ebecryl 81, ACTILANE 872, ACTILANE 735, ACTILANE 584, ACTILANE 525, ACTILANE 440, ACTILANE 432, ACTILANE 430, ACTILANE 423, ACTILANE 421 and ACTILANE 251.

The term "monofunctional" means one reactive functional group, e.g. acrylate, per monomer or oligomer and includes IBOA, Ebecryl 110, ODA-N and Ebecryl 1039. The term "polyfunctional" means more than one reactive functional group, e.g. acrylate, per monomer or oligomer and includes HDDA, DPGDA, TPGDA, TTEGDA, TMPTA and OTA 480.

Photoinitiators (ii) are necessary for free radical curing and may include, but are not limited to, the following compounds or combinations thereof: benzophenone and substituted benzophenones, 1-hydroxycyclohexyl phenyl ketone, thioxanones such as isopropylthioxanthone, 2-hydroxy-2-methyl-1-phenylpropan-1-one, 2-benzyl-2-dimethylamino-(4-morpholinophenyl)butan-1-one, benzil dimethylketal, bis(2,6-dimethylbenzoyl)-2,4,4-trimethylpentylphosphine oxide, 2,4,6-trimethylbenzoyldiphenylphosphine oxide, 2-methyl-1-[4-(methylthio)phenyl]-2-morpholinopropan-1-one, 2,2-dimethoxy-1,2-diphenylethan-1-one or 5,7-diiodo-3-butoxy-6-fluorone. Other useful photoinitiators are the so-called "cationic" type, which liberate a diffusible strong acid on exposure to ultra-violet light. Examples include

iodonium and sulfonium salts, such as diphenyliodonium fluoride and triphenylsulfonium hexafluorophosphate.

These may be sold under the Trade names of Irgacure 184, Irgacure 500, Darocure 1173, Irgacure 907, ITX, Lucerin TPO, Irgacure 369, Irgacure 1700, Darocure 4265, Irgacure 651, Irgacure 819, Irgacure 1000, Irgacure 1300, Esacure KT046, Esacure KIP150, Esacure KT37, Esacure EDB, H-Nu 470 and H-Nu 470X.

Colourants (iii) may be suitable dyes or preferably pigments selected for colour, dispersion or the other reasons. Colourants are well known in the art and include, but are not limited to those within the ranges having the following CI classifications: Green PG 7 and 36; Orange PO 5, 34, 36, 38, 43, 51, 60, 62, 64, 66, 67 and 73; Red PR-112, 149, 170, 178, 179, 185, 187, 188, 207, 208, 214, 220, 224, 242, 251, 254, 255, 260 and 264; Magenta/Violet PV 19, 23, 31 and 37 and PR 122, 181 and 202; Yellow PY 17, 120, 138, 155, 168, 175, 179, 180, 181 and 185; Blue PB 15; Black PB 2, 5 and 7. Examples of specific pigments include IRGALITE BLUE GLVO, MONASTRAL BLUE FGX, IRGALITE BLUE GLSM, HELIOGEN BLUE L7101F, LUTETIACYANINE ENJ, HELIOGENBLUE L6700F, MONASTRAL GNXC, MONASTRAL GBX, MONASTRAL GLX MONASTRAL 6Y, IRGZIN DPP ORANGE RA, NOVAPERM ORANGE H5G70, NOVAPERM ORANGE HL, MONOLITE ORANGE 2R, NOVAPERM RED HFG, HOSTAPERM ORANGE HGL, PALIOGEN ORANGE L2640, SICOFASST ORANGE 2953, IRGAZIN ORANGE 3GL, CHROMOPHTHAL ORANGE GP, HOSTAPERM ORANGE GR PV CARMINE HF4C, NOVAPERM RED F3RK 70, MONOLITE RED BR, IRGAZIN DPP RUBINE TR, IRGAZIN DPP SCARLET EK, RT-390-D SCARLET, RT-280-D RED, NOVAPERM RED HF4B, NOVAPERM RED HF3S, NOVAPERM RED HF2B, VYNAMON RED 3BFW, CHROMOPHTHAL RED G, VYNAMON SCARLET 3Y, PALIOGEN RED L3585, NOVAPERM RED BL, PALIOGEN RED 3880 HD, HOSTAPERM P2GL, HOSAPERM RED P3GL, HOSTAPERM RED E5B 02, SICOFASST RED L3550, SUNFAST MAGENTA 122, SUNFAST RED 122, SUNFAST VIOLET 19 228-0594, SUNFAST VIOLET 19 228-1220, CINQUASIA VIOLET RT-791-D, VIOLET R NRT-

201-D, RED B NRT-796-D, VIOLET R RT-101-D, MONOLITE VIOLET 31,
SUNFAST MAGENTA 22, MAGENTA RT-243-D, MAGENTA RT 355-D, RED B RT-
195-D, CINQUASIA CARBERNET RT-385-D, MONOLITE VIOLET R, MICROSOL
VIOLET R, CHROMOPHTHAL VIOLET B, ORACET PINK RF, IRGALITE YELLOW
5 2GP, IRGALITE YELLOW WGP, PV FAST YELLOW HG, PV FAST YELLOW H3R,
HOSTAPERM YELLOW H6G, PV FAST YELLOW, PALIOTOL YELLOW D1155
AND IRGZIN YELLOW 3R.

10 Synergist additives may be used to improve the curing quality and to diminish the
influence of the oxygen inhibition. Such additives include, but are not limited to
ACTILANE 800, Ebecryl P115, Ebecryl 350, ACTILANE 725, CD 1012 and DIDMA.

Surfactant additives are used primary to modify the surface tension of the inks. Such
additives include, but are not limited to ACTILANE 800, Tego glide 410, Tego glide
15 435, Tego glide 440, Tego glide 450, Tego flow 300, Tego flow 425, Tego flow ZFS460,
Tego rad 2100, Tego rad 2200 -N, Tego rad 2600, Tego rad 2700, Tego wet ZFS453,
Tego wet 250, Dow corning 67, SR 492, SR 9003, Surfadone 300, BYK 306, FC-430,
Fc-171, FC-431, Tego disperse 610, Tego disperse 710, anti terra-u, Disperbyk 108, anti
terra 204, EFKA 47 and EFKA 400.

20

Examples

In order to exemplify the present invention the following formulation was used:

25	Monofunctional acrylate	15 - 45 %
	Polyfunctional acrylate	45 - 55 %
	Photoinitiators	1.0 - 6.0 %
	Amine acrylate (Synergist additive)	< 5%
	Pigment dispersion	< 3%
30	Tegorad 2100 (Surfactant additive)	0.01-2.0%

Wet-on-wet printing was carried out using a Barco ink-jet (Dot factory) printer on a substrate of self-adhesive PVC foil.

5 Example 1

Inks having a gradient of viscosity of between 12 and 22 mPas across the colours C-M-Y-K were prepared and tested using wet-on-wet printing according to the printing process outlined above. To achieve the viscosity gradient the monofunctional to polyfunctional ratio was varied from 0.35 to 1.5.

The gradient of viscosity was varied from CYAN to BLACK starting at 12 mPas for CYAN and ending at 22 mPas for BLACK, using the following order for the colours:

- | | | |
|----|------------|---------|
| 15 | 1) CYAN | 12 mPas |
| | 2) MAGENTA | 14 mPas |
| | 3) YELLOW | 18 mPas |
| | 4) BLACK | 22 mPas |

20 This gave improved print results compared with inks having the same viscosity. In particular, there was there less mottling and puddling, the lines produced were sharper, and the colour was clearer.

Example 2

25

Inks having a gradient of viscosity of between 22 and 12 mPas across the colours C-M-Y-K were prepared and tested using wet-on-wet printing according to the printing process outlined above. To achieve the viscosity gradient the monofunctional to polyfunctional ratio was varied from 0.35 to 1.5.

30

The gradient of viscosity was varied from CYAN to BLACK starting at 22 mPas for CYAN and ending at 12 mPas for BLACK, using the following order for the colours:

- | | | |
|---|------------|---------|
| | 1) CYAN | 22 mPas |
| 5 | 2) MAGENTA | 18 mPas |
| | 3) YELLOW | 14 mPas |
| | 4) BLACK | 12 mPas |

As in Example 1, this gave improved print results compared with inks having the same
10 viscosity.

Example 3

15 Inks having a gradient of surface tension across the colours C-M-Y-K were prepared and tested using wet-on-wet printing according to the printing process outlined above. The surface tension ranged between 22 and 31 dynes/cm. The surface tension gradient was achieved by modifying the amount of surfactant additives added in the ink compositions from 0.02% to 0.8%.

20 A gradient of surface tension starting from CYAN at 22 dynes/cm and ending with BLACK at 31 dynes/cm was tested, using the following order for the colours:

- | | | |
|----|------------|-------------|
| | 1) CYAN | 22 dynes/cm |
| | 2) MAGENTA | 25 dynes/cm |
| 25 | 3) YELLOW | 28 dynes/cm |
| | 4) BLACK | 31 dynes/cm |

As in Example 1, this gave improved print results compared with inks having the same surface tension

30

Example 4

Inks having a gradient of surface tension starting from CYAN at 31 dynes/cm and ending with BLACK at 22 dynes/cm were also tested.

5

The inks were used in the following order:

- | | | |
|----|------------|-------------|
| | 1) CYAN | 31 dynes/cm |
| | 2) MAGENTA | 28 dynes/cm |
| 10 | 3) YELLOW | 25 dynes/cm |
| | 4) BLACK | 22 dynes/cm |

As in Example 1, this also gave improved print results compared with inks having the same surface tension.

15

Example 5

Inks having a gradient of cure speed over the colours C-M-Y-K were prepared and tested.

A range of cure speed between 30 and 50 m/minute were used, when measuring a 12 μ m film of ink coated onto rigid PVC and passed under a 120 W/cm. medium pressure UV mercury lamp was used. The cure speed gradient was varied by modifying the amount of photoinitiator and synergist additives. A gradient of speeds starting from CYAN at 30 m/min and ending with BLACK at 50 m/min were tested.

25 The inks were used in the following order:

- | | | |
|----|------------|----------|
| | 1) CYAN | 30 m/min |
| | 2) MAGENTA | 37 m/min |
| | 3) YELLOW | 45 m/min |
| 30 | 4) BLACK | 50 m/min |

As in Example 1, this gave improved print results compared with inks having the same cure speeds.

Example 6

5

Inks were prepared having a gradient of cure speed over the colours C-M-Y-K and tested. A range of cure speed between 50 and 30 m/minute were used, when measuring a 12 micron film of ink coated onto rigid PVC and passed under a 120 W/cm. medium pressure UV Mercury lamp was used. The cure speed gradient was prepared by

10

modifying the amount of initiators and synergist additives. A gradient of speeds starting from CYAN at 50 m/min and ending with BLACK at 30 m/min were used.

The inks were used in the following order:

15

1) CYAN

50 m/min

2) MAGENTA

43 m/min

3) YELLOW

36 m/min

4) BLACK

30 m/min

20

As in Example 1, this gave improved print results compared with inks having the same cure speeds.

Claims

1. A progressive dot printing ink-jet process comprising the steps of applying a first ink drop to a substrate and subsequently applying a second ink drop on to the first ink drop without intermediate solidification of the first ink drop, wherein the first and second ink drops have a different viscosity, surface tension or curing speed.
2. A progressive dot printing ink-jet process as claimed in claim 1, wherein further ink drops are applied sequentially to the combined first and second ink drops without intermediate solidification of the first and subsequent ink drops.
3. A progressive dot printing ink-jet process as claimed in claim 1 or 2, wherein at least four ink drops are applied sequentially.
4. A progressive dot printing ink-jet process as claimed in any preceding claim, wherein the first and subsequent ink drops are different colours.
5. A progressive dot printing ink-jet process as claimed claim 4, wherein the ink drops are cyan, magenta, yellow and black.
6. A progressive dot printing ink-jet process as claimed in any preceding claim, wherein the viscosity of the first and last ink drops applied varies in a graduated manner within a range of from 10 up to 30 mPas or 30 down to 10 mPas.
7. A progressive dot printing ink-jet process as claimed in any preceding claim, wherein the surface tension of the first and last ink drops applied varies in a graduated manner within a range of from 20 up to 40 dynes/cm or 40 down to 20 dynes/cm.
8. A progressive dot printing ink-jet process as claimed in any preceding claim, wherein the cure speed of the first and last ink drops applied varies in a graduated manner within a range of from 20 up to 70 m/min or 70 down to 20 m/min.

9. A set of ink-jet inks suitable for use in a progressive dot printing ink-jet process comprising at least two inks having a different viscosity, surface tension or curing speed.

5 10. A set of ink-jet inks as claimed in claim 9, wherein the ink-jet inks are cyan, magenta, yellow and black.

11. A set of ink-jet inks as claimed in claim 9 or 10, wherein the viscosity of the ink-jet inks varies in a graduated manner within a range of from 10 up to 30 mPas or 30 down to 10 mPas.

10

12. A set of ink-jet inks as claimed in any of claims 9 to 11, wherein the viscosity of the ink-jet inks varies in a graduated manner within a range of from 20 up to 40 dynes/cm or 40 down to 20 dynes/cm.

15 13. A set of ink-jet inks as claimed in any of claims 9 to 12, wherein the viscosity of the ink-jet inks varies in a graduated manner within a range of from 20 up to 70 m/min or 70 down to 20 m/min.

14. An ink dispenser holding a set of ink-jet inks as claimed in any of claims 9 to 13.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.